

Amendments to the Specification

Please amend the specification as follows:

On page 15, the first paragraph,

Dyeing prescription G

A dry mixture comprising 40% not bleached ground wood and 60% sulphite cellulose
~~Sulfitzellstoff~~ were beaten with water in a Holländer to a ground grad of 40 SR. The
suspension was thinned with water to comprise 2.5% of dry fibres.